

DO 1x200/280-306 JN1008 B-LA

Cable specification: JN1008, document M J61.610 Edition D; cable type B. Single Silica, step-index, multimode fiber in Silica
Suitable for nuclear radiation resistance



General airframe inter connection cable operating from -60°C up to +150°C



Cable characteristics



-60 +135°C



Excellent

Environmental

- Operating temperature: -60°C to 135°C
- Resistant to contamination and Aircraft fluids

Other characteristics

See page 2

Cable design



5
4 3 2 1

1. Optical fiber, step index F-S200/280 15B20
2. Coating: Silicone elastomer, black
3. Inner sheath: ETFE, black
4. Strength members: Aramid yarns
5. Sheath: ETFE colour violet

Identification

JN1008 B-LA
1 2 3

1. Part number
2. Cable type
3. Cable code

Marking

JN1008 M YY
1 2 3

1. Part number
2. Manufacturer's mark
3. Manufacturing year

Colour of cable: Violet

Specifications

Cable Specification

Specification JN1008, document M J61,610 Edition D; cable type B

Dimensional

Order reference	Core Ø	2. Coating Ø	Inner sheath	Strength members	Outer Ø	Weight
	µm	mm	mm	mm	mm	kg/km
DO 1x200/280-306	500±30	0.75±0.05	0.90-0.05	1.90±0.1	2.5± 0.15	7

Other characteristics

DO 1x200/280 - 306

Cable fibre attenuation	λ= 850nm	+55nm -40nm	≤ 20.0 dB/km
Temperature Cycling IEC 793 – 1 D1	-60°C + 150°C during cycling after test at ambient temperature		Attenuation variation ≤ ± 0.5 dB ≤ ± 0.2 dB
Tensile performance BS 6558 part1, clause E3	Applied tension 650 N	Elongation ≤ 0.1 %	Attenuation variation No after test
Cable twist bend DOD-STD 1678, method 2060, proc.1 No fibre break	Diameter 25 mm	Nb of cycles 2000	Tensile force 100 N
Minimum bending radius DIN VDE 0472, part 232	Diameter 60 mm	Nb of turns 5	Attenuation variation ≤ ± 0.8 dB
Repeated bending IEC 794-1, clause E 6 No fibre break	Diameter 12.5 mm	Nb of turns 500	Tensile force 50 N
Crush load BS 6658, clause E 9	Load 150N for 5 min	R 12.5mm - 3.0mm	Attenuation variation ≤ ± 0.1 dB ≤ ± 1.0 dB
Compressive strength IEC 794 –1 clause E3	Load Initially 5000N/ 100mm 2000N/100m for 5 min		Attenuation variation ≤ ± 0.5 dB
Impact (R = 50mm) DOD-STD-1678, method 2030, proc.2 No splitting or cracking	5 tests 20 impacts	Start energy 1 Nm	Attenuation variation ≤ ± 0.2 dB after test
“no attenuation variation” means	The measured value is within the measuring ($\Delta\alpha \leq \pm 0.05$ dB)		
Flammability	As EFA document SPE-J-920-A0061 Part C		Compliant



Prysmian câbles et systèmes France

Head Office

23 avenue Aristide Briand - BP 801 - PARON - 89108 SENS Cedex / France
Tel : +33 (0)4 72 46 73 99 - infocables.fr@prysmian.com

Draka Fileca SAS

D 1001 - 60730 Sainte-Geneviève / France
fileca-office@prysmian.com



www.prysmian.com



© PRYSMIAN 2024

All Rights Reserved. The information contained within this document must not be copied, reprinted or reproduced in any form, either wholly or in part, without the written consent of Prysmian. The information is believed correct at the time of issue. Prysmian reserves the right to amend this specification without notice. This specification is not contractually valid unless specifically authorised by Prysmian.